



TECHNICAL SHEET

PETOL[®] 160-3

POLYETHER POLYOL

Last revision 2018

Chemical Name: Polyether – Polyol
Abbreviation: Petol 160-3

General Description:

PETOL 160-3 is a polyoxypropylene triol, 1055 average molecular weight.

Technical Quality Conditions:

Characteristics	MU	Values	Test methods
Appearance	-	clear, viscous liquid	visual
Hydroxyl value	mg KOH/g	150-170	ASTM D 4274
Acid value (ABT), max	mg KOH/g	0.05	ILL 003/3-23
Viscosity, at 25 °C	cP	240-300	ASTM D 4878
Water (Karl-Fischer), max.	%	0.08	ASTM E 203
Content in Na and K, max	ppm	10	ILL 003/3-12

Specific Properties:

Density at 25°C, g/cm ³	1.018
Functionality	3
Ignition temperature, °C min.	min.200
pH	4.5-6.5

The specific properties present approximate values and contain general information, without being part of the technical quality conditions.

Main Applications:

- standard polyol for one-component spray foams
- flexiblensness agent for epoxy resins;
- can be used in polyol blends in the manufacture of coatings, polyurethane adhesives and special polyurethane foams
- hydraulic fluids, lubricants.



S.C. CHIMCOMPLEX S.A. BORZEȘTI - ROMÂNIA

Sucursala Râmnicu Vâlcea

✉: Str. Uzinei, nr. 1, Râmnicu Vâlcea, jud. Vâlcea
Tel: +40 250 701 200; Fax: +40 250 735 030
www.chimcomplex.ro

Packing and storage:

The product is packed in stainless steel or coated rail or road tanks, property of supplier or client. Due to its hygroscopic nature, the product is stored in tightly closed containers under nitrogen blanket, in cold, dry, vented areas, far from heat, moisture and inconsistent materials, at temperatures between +20°C and +30°C.

Safety Considerations:

Before handling and using of product, the personnel must be aware of the dangers implied. This information is available in SDS and on the product label.

Attention:

Please contact CHIMCOMPLEX BORZESTI-Ramnicu Valcea Branch to see if the document has been revised and for any other additional information related to the product.

Important:

For a better suitability of the product for your particular purpose, tests are recommended prior product use. You are advised to make your own determination as to safety, appropriate manner of handling, storage, use and disposal. All the information contained in this product technical sheet is offered for your consideration, investigation and verification. The data is presented in good faith and is believed to be reliable. You should not consider the descriptions, information, data or design as a part of our terms and conditions of sale. We expressly disclaim responsibility or liability for any loss, damage or expense arising out of reliance on the information provided herein.