



TECHNICAL SHEET

PETOL PM[®] 410-4N

POLYETHER POLYOL

Last revision 2018

Chemical Name: Propoxilated Mannich Base
Abbreviation: Petol PM 410-4N

General Description:

Petol PM 410-4N is a Mannich polyol used in polyol blends to obtain rigid foams blown with water for pipe insulation and sprayed rigid foams.

Technical Quality Conditions:

Characteristics	MU	Values	Test methods
Appearance	-	clear, viscous liquid	visual
Hydroxyl number	mg KOH/g	400-440	ASTMD 4274
Viscosity, 25 °C	cP	8000-15000	ASTM D 4878
Water (Karl-Fischer), max	%	0.1	ASTME 203

Specific Properties:

Density at 25°C, g/cm ³	1.01-1.10
Functionality	4
Molecular weight	530
Ignition temperature, min.	200°C

The specific properties present approximate values and contain general information, without being part of the technical quality conditions.

Major Applications:

- sprayed or moulded rigid polyurethane foams.



S.C. CHIMCOMPLEX S.A. BORZEȘTI - ROMÂNIA
Sucursala Râmnicu Vâlcea

✉: Str. Uzinei, nr. 1, Râmnicu Vâlcea, jud. Vâlcea
Tel: +40 250 701 200; Fax: +40 250 735 030
www.chimcomplex.ro

Packing and storage:

The product is packed in stainless steel or inner coated rail or car tanks, property of supplier or client. Due to its hygroscopic nature, the product is stored in tightly closed containers under nitrogen blanket, in cold, dry, vented areas, far from heat, moisture and inconsistent materials, at temperatures between +20°C and +30 °C.

Safety Considerations:

Before handling and using of product, the personnel must be aware of the dangers implied. This information is available in SDS and on the product label.

Attention:

Please contact CHIMCOMPLEX BORZESTI-Ramnicu Valcea Branch to see if the document has been revised and for any other additional information related to the product.

Important:

For a better suitability of the product for your particular purpose, tests are recommended prior product use. You are advised to make your own determination as to safety, appropriate manner of handling, storage, use and disposal. All the information contained in this product technical sheet is offered for your consideration, investigation and verification. The data is presented in good faith and is believed to be reliable. You should not consider the descriptions, information, data or design as a part of our terms and conditions of sale. We expressly disclaim responsibility or liability for any loss, damage or expense arising out of reliance on the information provided herein.